



TwinBond SFA-100 SIP 2K Fast

REINFORCING IMPREGNATION FOR FACADE PANELS

- ✓ Short drying time
- ✓ For most fibre cement boards
- ✓ Elastic
- ✓ Moisture and chemical resistant



Technical Info

- Technology: 2K epoxy.
- Colour: light yellow transparent.
- Density at +20°C: 1.07 g/cm³.
- Application temperature: between +5°C and +40°C.
- Working time (20°C): 60 min.
- Flammable: no.
- VOC: < 30%.
- Consumption: 3m²/kg.
- Shelf life: 12 months, dry, cool and frost-free in original closed packaging.

Packing

TwinBond SFA-100 SIP 2K Fast - 1kg

550326924

Product

Characteristics

Universal 2-component synthetic resin-based reinforcement for fibre-cement façade panels. SIP 2K Fast is easy to apply by brush or roller and guarantees a strong, durable bonding surface.

Use

- Mix A and B components completely to a homogeneous mass. For small applications, carefully mix 1 volume of A component with 1 volume of B component.
- Process within 60 minutes after mixing.
- Apply on clean and dry surfaces with roller or brush.

Minimum processing temperature: +5°C.

After at least 2 hours, test the curing by using TwinBond Tape. If the tape adheres sufficiently, the treated surface is ready for

bonding.
Full chemical resistance after 7 days.